


## DETAIL: TPO Low Slope Roof

### GENERAL DETAILS – SEAMS – ROOF COATING RESTORATION

This detail drawing is intended to show the generally recommended procedure for dealing with the condition shown. Actual field conditions may vary. When such conditions vary slightly from the drawing, the intent and industry best practices are to be used. Any question, contact Aldo Products Company, Inc., Technical Department.



1. Apply the ALDOSEAL product of choice at a minimum rate of 50 wet mils, extending at least 6" on either side of the seam.
2. Ensure that product fills any seam void or opening completely.
3. Feather product out from seam to create positive water drainage.

Option: If required by specification, ALDOSEAL fabric is used in a three course application method with ALDOSEAL product of choice. Contact Aldo Products Company, Inc., for assistance.