



# ALDOCOAT 910

## RUBBER SKYLIGHT COATING

### TYPICAL PHYSICAL PROPERTIES

COLOR .....	CLEAR
COVERAGE RATE.....	80 - 100 SF/GAL
WET MIL THICKNESS.....	10 – 12 MILS
DRY MIL THICKNESS.....	4 – 5 MILS
FLASHPOINT .....	101°F
SPECIFIC GRAVITY .....	864
WEIGHT (LB./GAL.).....	7.2
SOLIDS (% BY WEIGHT).....	37.1 ± 1%
VISCOSITY @ 78° .....	1,500 CPS
ELONGATION .....	ASTM D-412....400%
TENSILE STRENGTH .....	ASTM D-412....1520 PSI
PERMEANCE (10 MILS) .....	0.166 PERMS
DRYING TIME.....	1 – 3 HOURS

### PRODUCT DESCRIPTION

**ALDOCOAT 910 Rubber Skylight Coating** a proprietary chemical formula with built-in strength and water resistance for extremely effective protection for fiberglass skylight panels. **ALDOCOAT 910** is a one component, clear rubber coating that has excellent adhesion to properly prepared surfaces and is thermally stable and resists cracking and peeling due to weather extremes and ultraviolet exposure.

### GENERAL SURFACE PREP

**ALDOCOAT 910** may be applied by medium nap rollers, soft brushes or conventional airless spray equipment. The surface must be free of any oils, moisture, rust scale, soil or other contaminants that may interfere with good adhesion. Remove any loose material from seams or other surfaces with a wire brush or scraper. Oil and grease should also be removed with solvents or an appropriate detergent cleaner. In many cases high pressure water blast will be sufficient to prepare the surface.

For best results, apply **ALDOCOAT 910** when ambient air and the substrate is within 50 – 100°F. For best spray application, the product should be at a minimum of 60°F. Lower temperatures can be utilized for brush.

### LIMITATIONS AND PRECAUTIONS

**ALDOCOAT 910** contains a blend of solvents which is considered combustible by D.O.T. and O.S.H.A. standards. It should be used and stored away from flames, in a well-ventilated atmosphere. Avoid prolonged breathing of vapors and prevent contact with eyes. Read all label information and precautions before using.

The specifications, properties and performance of materials described herein are based on information believed to be reliable. Unless otherwise expressly provided in written contract, the products discussed are sold without conditions or warranties, expressed or implied. Product specifications are subject to change without notice.

