



ALDOCOAT 916

RUBBER ROOF COATING

TYPICAL PHYSICAL PROPERTIES

COLOR.....	WHITE
COVERAGE RATE.....	65-100 SF/GAL
FLASHPOINT.....	101°F
WEIGHT (LB./GAL.).....	9
SOLIDS (% BY WEIGHT).....	57.0±1%
VISCOSITY @ 78°	4800 CPS
DRYING TIME.....	2 – 4 HOURS
ELONGATION	400%
TENSILE STRENGTH	ASTM-D 412..1200 PSI

Recommended Spray Equipment = Airless

TIP SIZE.....	0.025"
FLUID PRESSURE (PSI)	3000
FLUID HOSE SIZE.....	3/8" – 1/2"

PRODUCT DESCRIPTION

ALDOCOAT 916 is specifically designed for metal roofs with its rust inhibiting properties. This one-coat application provides excellent waterproofing and ultraviolet resistance by creating a flexible, seamless membranes. It is thermally stable and resists cracking and peeling due to weather extremes. **ALDOCOAT 916** controls corrosion and rust bleed through, even after years of service.

GENERAL SURFACE PREP

ALDOCOAT 916 may be applied by medium nap rollers, soft brushes or conventional airless spray equipment. The surface must be free of any oils, moisture, rust scale, soil or other contaminants that may interfere with good adhesion. Remove any loose material from seams or other surfaces with a wire brush or scraper. Oil and grease should also be removed with solvents or an appropriate detergent cleaner. In many cases high pressure water blast will be sufficient to prepare the surface.

For best results, apply **ALDOCOAT 916** when ambient air and the substrate is within 50 – 100°F. For best spray application, the product should be at a minimum of 60°F. Lower temperatures can be utilized for brush.

LIMITATIONS AND PRECAUTIONS

ALDOCOAT 916 contains a blend of solvents which is considered combustible by D.O.T. and O.S.H.A. standards. It should be used and stored away from flames, in a well-ventilated atmosphere. Avoid prolonged breathing of vapors and prevent contact with eyes. Read all label information and precautions before using.

The specifications, properties and performance of materials described herein are based on information believed to be reliable. Unless otherwise expressly provided in written contract, the products discussed are sold without conditions or warranties, expressed or implied. Product specifications are subject to change without notice.