



ALDOCOAT 918

SINGLE-PLY TOP COAT

TYPICAL PHYSICAL PROPERTIES

COLOR	WHITE
COVERAGE RATE.....	65-100 SF/GAL
FLASHPOINT	101°F
WEIGHT (LB./GAL.).....	9
SOLIDS (% BY WEIGHT).....	56.0±1%
VISCOSITY @ 78°	4800 CPS
DRYING TIME.....	2 – 4 HOURS
ELONGATION	400%
TENSILE STRENGTH	1200 PSI

TYPES OF APPLICATIONS

- TPO
- Hypalon
- EPDM
- Modified Bitumen
- Built-up Roofs
- Urethane Foam

Recommended Spray Equipment = Airless

TIP SIZE.....	0.025"
FLUID PRESSURE (PSI).....	3000
FLUID HOSE SIZE	3/8" – 1/2"

PRODUCT DESCRIPTION

ALDOCOAT 918 Single-Ply Top Coat provides excellent waterproofing and ultraviolet resistance on various roofing surfaces. **ALDOCOAT 918** has high solar reflectance for increased energy savings and is thermally stable to resist cracking and peeling due to weather extremes. **ALDOCOAT 918** can be applied over various base coats.

GENERAL SURFACE PREP

ALDOCOAT 918 may be applied by medium nap rollers, soft brushes or conventional airless spray equipment. The surface must be free of any oils, moisture, rust scale, soil or other contaminants that may interfere with good adhesion. Remove any loose material from seams or other surfaces with a wire brush or scraper. Oil and grease should also be removed with solvents or an appropriate detergent cleaner. In many cases high pressure water blast will be sufficient to prepare the surface.

For best results, apply **ALDOCOAT 918** when ambient air and the substrate is within 50 – 100°F. For best spray application, the product should be at a minimum of 60°F. Lower temperatures can be utilized for brush.

LIMITATIONS AND PRECAUTIONS

ALDOCOAT 918 contains a blend of solvents which is considered combustible by D.O.T. and O.S.H.A. standards. It should be used and stored away from flames, in a well-ventilated atmosphere. Avoid prolonged breathing of vapors and prevent contact with eyes. Read all label information and precautions before using.

The specifications, properties and performance of materials described herein are based on information believed to be reliable. Unless otherwise expressly provided in written contract, the products discussed are sold without conditions or warranties, expressed or implied. Product specifications are subject to change without notice.