



Stop the **leaks!** Reflect the **heat!**
Lower energy **bills!** Save **money!**



TECHNICAL DATA SHEET

ALDOCOAT 374 CONTRACTOR GRADE ACRYLIC

PRODUCT DESCRIPTION:

ALDOCOAT 374 is a high solids, technologically advanced, fire retardant, thixotropic, 100% acrylic elastomeric uniquely formulated for the protection of spray polyurethane foam, metal, and a wide variety of other substrates. The proprietary formulation incorporates high solids elastomeric acrylic resins, reinforcing laminar pigments and non-migrating fire retardants to produce a seamless, flexible, durable membrane having exceptional weather ability, ultraviolet and fire resistance. **ALDOCOAT 374** acts as a “breathing” membrane allowing trapped moisture vapor to pass through the film while remaining impervious to exterior mass water penetration. The resultant tough, cured film provides good resistance to mechanical damage and chemical attack

RECOMMENDED USES:

ALDOCOAT 374 is the ideal choice for metal roofs, BUR and single ply restoration. This product carries the **FM Global Approval (ASTM E108)** over spray polyurethane foam and **FM Severe Hail Rating (Class 1SH)** over metal decks. The thixotropic nature of **ALDOCOAT 374** permits high build coverage, even on rough, textured or vertical surfaces without pin holing or sagging. It also has excellent adhesion to a variety of other substrates, such as asphalt, primed wood, primed metal, concrete and masonry. **Ponding water conditions are to be avoided.** Please contact our Technical Service Department for primer recommendations for application over rusted surfaces.

GENERAL APPLICATION INSTRUCTIONS:

ALDOCOAT 374 may be applied by medium nap rollers, brushes or airless spray equipment. Airless spray is the most efficient application method for larger projects. Brushes and rollers may be used for detail work such as edge termination, filling of voids, pinholes and small cracks. Apply **ALDOCOAT 374** only to clean and dry sound substrates free of loose particles or other foreign matter. **ALDOPRIME 708** Acrylic or **ALDOPRIME 710** Rust Inhibitor may be required subject to type of substrate to maximize adhesion and/or lock in rust. Contact our Technical Service Personnel for project specific primer recommendations and substrate preparation. **SOME SEPARATION MAY OCCUR DURING SHIPMENT AND STORAGE. THEREFORE, THE CONTENTS OF EACH CONTAINER SHOULD BE THOROUGHLY POWER MIXED FOR THREE (3) TO FIVE (5) MINUTES. DO NOT THIN PRODUCT.** It is recommended that **ALDOCOAT 374** be sprayed in multiple coats applied in multidirectional passes (north-south/east-west) to insure uniform film build and to avoid pinholing. Backrolling sprayed material may be necessary to fill pinholes in substrate. Final dry film thickness (DFT) is to be a minimum of 25 dry mils and free of voids, pinholes, holidays, cracks or blisters. **COATING APPLICATION SHOULD BE SUSPENDED IMMEDIATELY AND OUR TECHNICAL SERVICE PERSONNEL CONTACTED IF THE RESULTS BEING OBTAINED ARE LESS THAN DESIRABLE.**

1604 N. MAIN ST, KANNAPOLIS, NC 28081 ALDOPRODUCTS.COM OFFICE (800) 474-6019 FAX (704) 932-3041

TYPICAL PHYSICAL PROPERTIES

TOTAL SOLIDS: 68% by weight ASTM D1644
60% by volume ASTM D2697

WEIGHT PER GALLON: 11.4 lbs per gallon ± 0.2

SHELF LIFE: 12 months @ 45°- 80° F

COLOR: White, Gray or as specified

VISCOSITY: 8000 ± 1500 cP

ELONGATION: 315% ASTM D412

RECOVERY: 100% ASTM D412

IMPACT RESISTANCE: exceeds 160b in/lb.
ASTM D-2294

HARDNESS: 45 Shore A ASTM D-2240

TENSILE STRENGTH: 400 psi; 3600 psi w/ fabric
ASTM D-412

PERMEABILITY: 3.4 perms ASTM E-96

ALGAE RESISTANCE: No growth supported
ASTM G29-96

FUNGI RESISTANCE: No growth supported
ASTM G29-96

SALT SPRAY: No effect (3000 hours)
ASTM B-117

WEATHERABILITY: No effect (3800 hours)
ASTM G-26

SERVICE TEMPERATURE: -40° TO 200° F

FIRE RATING: FM Global Approved

HAIL RATING: FM Severe Hail Rating FM Class

CURE TIMES: DRY TO TOUCH: 4 Hours @ 75° F
TACK FREE: 12 Hours
RECOAT: 12-24 Hours

SOLAR REFLECTANCE: .82
THERMAL EMITTANCE: .90

EPA Energy Star Listed



ALDOCOAT 374 CONTRACTOR GRADE ACRYLIC

Apply two (2) or more coats of **ALDOCOAT 374** at the rate of 1-2 gallons per 100 square feet. As a visual aid in the application of the product, **ALDOCOAT 374** gray may be used. Darker colors are available and may accelerate the curing process in cooler ambient temperatures. Accentuated surface profiles that increase total surface area will require a proportionate increase in the amount of **ALDOCOAT 374** to satisfy the minimum dry mil thickness specification requirements. If specification calls for roofing granules, these may be broadcast into intermediate coat or within 10 minutes of final coat application at the rate of 35 - 40 pounds per 100 square feet. No foot traffic should be permitted on the coated surface for 72 hours after application.

GENERAL APPLICATION INSTRUCTIONS OVER METAL:

ALDOCOAT 374 may be applied to all types of metal substrates, including surfaces previously coated with aluminized asphalt or other similar acrylic coatings. Apply **ALDOCOAT 374** only to clean, dry, sound surfaces free of loose particles or other foreign matter. Surface should be thoroughly inspected for oxidation. Conditions of all seams, fasteners and flashing areas should be checked for gaps, pinholes or

cracks. Pressure washing is required as the initial step in the preparation of the substrate. All seams are to be sealed, fastener heads addressed and all roof penetrations inspected as well for possible water penetration. Strict adherence to the published ALDO Metal Roof Restoration Specification or consultant/architect specification is required. ALDO Products Company, Inc., is not responsible for building engineering or structural design issues, internal or external. Please consult a building professional if such issues are suspected of having an affect on any roof restoration process.

LIMITATIONS AND PRECAUTIONS:

ALDOCOAT 374 is a water based elastomeric acrylic coating that will freeze and become unusable at temperatures below 32° F. **PROTECT FROM FREEZING DURING SHIPMENT AND STORAGE.** Do not store material at temperatures below 45° F. Do not apply when ambient air and substrate temperatures fall below 50° F or when there is a possibility of temperatures dropping below 32° F within a 24 hour period after application. Do not apply over wet substrates or in inclement weather. Total cure of **ALDOCOAT 374** requires complete evaporation of water. Cool temperatures and high humidity retard cure. Coatings can cause a premature artificial dew zone during the cure process under certain climatic conditions. This is generated as the water in the coating evaporated, cooling the surface and attracting moisture in the form of dew. Therefore, it is imperative not to apply the product if climatic conditions prevent complete cure before rain, dew or freezing temperatures. **ALDOCOAT 374** is not a vapor barrier coating and is not recommended for use over cold storage installations. Where a vapor barrier is required, contact our Technical Service Personnel for proper selection and installation procedures. Use of acrylic coatings in darker colors over metal substrates may result in blistering.